

Technical fabric in natural flax fibre designed from non-coated twisted strands



Characteristics	Data
Width	1500 mm
Drapeability	Bonne
Thermal degradation	> 230°C
Packaging	Roll of 50 m
Mechanical properties ISO 527	VARIM process & TP resin - Vf=50 %
• Tensile strenght	100 MPa
• Tensile module (Young)	10 GPa

Available range

Code	Désignation	TwinFlax® / Laize 1500 mm
HC06C294	TwinFlax 2D 235	Fabrics bi-directionnel - Flax fibres - 235 g/m ²
T294/PA11	TwinFlax P-Preg PA11 500	Pre-preg fabrics - 50% weight - 500 g/m ²
T294/PP	TwinFlax P-Preg PP 500	Pre-preg fabrics - 50% weight - 500 g/m ²



TWINFLAX P-PREG
DA11

Agrobiobase Award

Product applications

Lay up, infusion, Resin Transfer Molding, film stacking

For more information : contact@flaxtechnic.com